



HIGH STRENGTH CONCRETE

ProMasonry High Strength Concrete is a blend of Portland cement, sand and stone that meets or exceeds ASTM C387 specification for compressive strengths when used as directed.

SUGGESTED USES

- Footings, foundations, steps, sidewalks, post holes, patios, floor slabs or any general concrete applications where a thickness greater than 2 inches (50 mm) is required.

PREPARATION

- Compact and moisten the base material.
- Place forms and reinforcing steel as needed.
- When repairing concrete, remove all loose and/or deteriorated material as well as any surface contaminants such as oil, paint, grease, etc.

MIXING

- Empty the contents of the bag into a clean wheelbarrow, mortar box, mechanical mixer or other mixing vessel.
- Form a crater with a shovel or hoe in the center of the dry mix. Pour the recommended 3.5 quarts (3.3 L) of clean potable water into the crater.
- **Caution** – An excessive amount of water will weaken the mix and can result in cracking. Add small quantities, 1 pint (0.5 L) or less, of water and thoroughly mix to reduce stiffness.
- **For hand mixing** – Blend dry mix with a shovel or hoe from the outer edges working the material towards the center. Continue mixing until all free water is used and all the aggregate is uniformly coated with cement.
- **For mechanical mixing** – Mix the material for three minutes.

PLACEMENT

- Place material until it slightly overfills the forms.
- Consolidate to remove any voids by using manual or mechanical vibration.
- Strikeoff with a screed or straight edge board.

FINISHING

- Allow bleedwater to evaporate before finishing.
- Use a float to achieve a smooth finish or a broom for a rougher surface.
- **Caution** – Overworking could weaken the surface and result in cracking, dusting or scaling.

CURING

- Dampen with a fine mist of water for 24 hours or moist cure with wet burlap and polyethylene.
- Alternatively, apply **ProMasonry Cure & Seal**.
- Protect from direct sunlight, wind, rain and frost during the curing period.

CLEAN UP

- Clean tools and equipment with water immediately after use.
- Cured material will need to be mechanically removed.



A Division of
Conproco Corporation

PROMASONRY[®]
PROFESSIONAL QUALITY CEMENT PRODUCTS



HIGH STRENGTH CONCRETE

TECHNICAL DATA

Physical state and appearance		Dry powder with aggregate	
Base		Portland cement	
pH	Wet mix	> 12	
Aggregate type		Concrete sand with 3/8 inch pea stone	
Slump	ASTM C143	2 inch (50 mm) – 3 inch (76 mm) @ 3.5 quarts (3.3 L) – water/bag	
Compressive strengths – psi	ASTM C387	7 Days 2,700 (18.6 MPa)	28 Days 4,000 (27.6 MPa)

YIELD

- One 80 lb. (36.3 kg.) bag yields approximately 0.6 cu. ft. (17.0 L).

CAUTION

- May cause eye and skin irritation.

HEALTH AND SAFETY

- Product is alkaline.
- Do not ingest.
- Avoid breathing dust.
- Avoid contact with skin and eyes.
- Refer to Material Safety Data Sheet (MSDS) for additional information.
- Keep out of reach of children.

FIRST AID

- In case of skin contact, wash thoroughly with soap and water.
- For eye contact, flush immediately with a high volume of water for at least 15 minutes and contact a medical professional.
- For respiratory problems remove person to fresh air.

DISPOSAL

- Dispose of material in accordance with local, state or federal regulations.

MANUFACTURER'S LIMITED WARRANTY

Conproco Corp. warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for use and assumes all risks.

Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. March 2011

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CONPROCO CORP. SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

PROMASONRY®

MANUFACTURED BY: **CONPROCO CORPORATION**

PHONE 800.258.3500 FAX 603.743.5744 WEBPROMASONRY.NET